

**Test Report**

Number: SHAH0163027301

Applicant: DXRACER TECHNOLOGY WUXI CO.,LTD  
17TH FLOOR BUILDING C UNIT 2, NO.108  
HUISHAN AVENUE, HUISHAN DISTRICT, WUXI  
CITY, JIANGSU PROVINCE  
Attn: LILY WU

Date: 16 Nov, 2023

Sample Description:

One( 1 ) piece of submitted sample said to be :  
Item Name : microfiber synthetic leather.  
Country Of Origin : China.


Tests Conducted:

As requested by the applicant, for details refer to attached page(s).

Conclusion:

Tested Samples	Standard	Result
Submitted Samples	Applicant's Requirement On Abrasion Resistance	Pass
Submitted Samples	Applicant's Requirement On Colour Fastness To Light	Pass
Submitted Samples	Tensile Strength	See Test Conducted
Submitted Samples	Tearing Strength	See Test Conducted
Submitted Samples	Bursting Strength	See Test Conducted
Submitted Samples	Air Permeability	See Test Conducted
Submitted Samples	Applicant's Requirement On Colour Fastness To Rubbing	Pass
Submitted Samples	Applicant's Requirement On Colour Fastness To Water	Pass
Submitted Samples	Applicant's Requirement On Colour Fastness To Perspiration	Pass

Prepared And Checked By:  
For Intertek Testing Services Wuxi Ltd.



Bill Zhang  
General Manager



## Test Report

Number: SHAH0163027301

### Tests Conducted

1 Abrasion Resistance

Test Standard: ISO 12947-2:1998 Martindale Abrasion And Pilling Tester, 9 kPa Total Weight

Resistance Face Side

Client's Requirement

Specimen 1

Over 20000 cycles

20000 cycles

Specimen 2

Over 20000 cycles

Specimen 3

Over 20000 cycles

Quoted Result

Over 20000 cycles

Date Sample Received: 08 Nov, 2023

Testing Period: 08 Nov, 2023 To 16 Nov, 2023

2 Colour Fastness To Light (ISO 105 B02-2014, Exposure Cycle A1, Xenon-Arc Lamp):

Up To Grade 4

Client's Requirement

Grade

4

4

Date Sample Received: 08 Nov, 2023

Testing Period: 08 Nov, 2023 To 16 Nov, 2023

3 Tensile Strength

Test Standard: ISO 13934-2: 2014, grab method.

Warp

1240.7N

Weft

880.0N

Date Sample Received: 08 Nov, 2023

Testing Period: 08 Nov, 2023 To 16 Nov, 2023

4 Tearing Strength As Received (ISO 13937-1:2000, Elmendorf Tear Tester):

Across Warp

>64N

Across Weft

61.3N

Date Sample Received: 08 Nov, 2023

Testing Period: 08 Nov, 2023 To 16 Nov, 2023

5 Bursting Strength As Received

Test Standard: ISO 13938-1:2019, Mullen Type Burster, Test Area, 30.5 mm Diameter:

2647.8Kpa

Date Sample Received: 08 Nov, 2023

Testing Period: 08 Nov, 2023 To 16 Nov, 2023

\*\*\*\*\*



## Test Report

Number: SHAH0163027301

### Tests Conducted

6 Air Permeability As Received (ISO 9237-1995):

NIL

Remark: Test Pressure= 200Pa  
Test Area = 20 cm<sup>2</sup>

Date Sample Received: 08 Nov, 2023  
Testing Period: 08 Nov, 2023 To 16 Nov, 2023

7 Colour Fastness To Rubbing

Test Standard: ISO 105 X12-2016

Dry	4-5	Client's Requirement
Wet	4-5	4

4

Date Sample Received: 08 Nov, 2023  
Testing Period: 08 Nov, 2023 To 16 Nov, 2023

8 Colour Fastness To Water

Test Standard: ISO 105 E01-2013

Color Change	4-5	Client's Requirement
Color Staining		4
-Acetate	4-5	
-Cotton	4-5	
-Nylon	4-5	
-Polyester	4-5	
-Acrylic	4-5	
-Wool	4-5	

4

Date Sample Received: 08 Nov, 2023  
Testing Period: 08 Nov, 2023 To 16 Nov, 2023

9 Colour Fastness To Perspiration

Test Standard: ISO 105 E04-2013

	Acid	Alkaline	Client's Requirement
Color Change	4-5	4-5	4
Color Staining			
-Acetate	4-5	4-5	
-Cotton	4-5	4-5	
-Nylon	4-5	4-5	
-Polyester	4-5	4-5	
-Acrylic	4-5	4-5	
-Wool	4-5	4-5	

4

Date Sample Received: 08 Nov, 2023  
Testing Period : 08 Nov, 2023 To 16 Nov, 2023

\*\*\*\*\*



**Test Report**

Number: SHAH0163027301

Tests Conducted

Photo



\*\*\*\*\*  
End Of Report

*The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band  $w = U$ ) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.*

*The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) received and tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Wuxi Ltd.*

